

AB-4655/61

AIR FORCE MATERIALS LABORATORY  
RESEARCH AND TECHNOLOGY DIV S109  
AIR FORCE SYSTEMS COMMAND

CONTRACT AF 33(615)-2000  
PROJECT 7361; TASK 736103

AB 465161

SILICON CARBIDE


Data Sheets

M. Neuberger

Approved for public release; distribution is unlimited.

DS-145

June 1965



**ELECTRONIC  
PROPERTIES  
INFORMATION  
CENTER**

HUGHES

HUGHES AIRCRAFT COMPANY  
CULVER CITY CALIFORNIA

85

NOTICE

If Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

Qualified requesters may obtain copies of this report from the Defense Documentation Center (DDC), Cameron Station, Bldg. 5, 5010 Duke Street, Alexandria, Virginia, 22314. ~~The distribution of this report is limited because the report contains technology identifiable with items on the strategic embargo lists excluded from export or re-export under U.S. Export Control Act of 1949 (63 STAT 7), as amended (50 U.S.C. App. 2026, 2031), as implemented by DDCR 400-10.~~

Approved for public release; distribution is unlimited.

Copies of this report should not be returned to the Research and Technology Division, Wright-Patterson Air Force Base, Ohio, unless return is required by security considerations, contractual obligations, or notice on a specific document.


SILICON CARBIDE

Data Sheets

M. Neuberger

DS-145

June 1965



**ELECTRONIC  
PROPERTIES  
INFORMATION  
CENTER**

**HUGHES**

HUGHES AIRCRAFT COMPANY  
CULVER CITY CALIFORNIA

## FOREWORD

This report was prepared by Hughes Aircraft Company under Contract No. AF 33 (615)-2460. The contract was initiated under Project No. 7381, Task No. 738103. The work was administered under the direction of the Air Force Materials Laboratory, Research and Technology Division, with Mr. R. F. Klinger acting as Project Engineer.

The Electronic Properties Information Center has been established to collect, index and abstract the literature on the electrical and electronic properties of materials and to evaluate and compile the experimental data from that literature. A modified coordinate index to the literature is machine-stored and printed for manual use. The Center published summary reports, thesauri, glossaries, data sheets and similar publications as sufficient information is evaluated and compiled. This report consists of the compiled data sheets on Silicon Carbide.

Many persons have contributed to the program which this report represents. The author wishes especially to acknowledge the contributions of the following: John W. Atwood, C.L.M. Blocher, D. Gough, D.L. Grigsby, D.H. Johnson, H. Thayne Johnson, Thomas J. Lyndon, J.T. Milek, Emil Schafer and C.A. Schill.

Special thanks are extended to Dr. J. J. Grossman for his efforts in reviewing all technical data prior to publication.

## ABSTRACT

These data sheets present a compilation of a wide range of electrical, optical and energy values for alpha and beta-silicon carbide in bulk and film form. Electrical properties include conductivity, resistivity, dielectric constant, Hall coefficient, mobility, lifetime and thermoelectric effects. Emission data have been broken down into the varied electron and photon emissions which result from application of energy in the electromagnetic spectrum. Energy data include energy bands, energy gap and energy levels for variously-doped silicon carbide, as well as effective mass tables, work function, and cross sections. The optical properties include absorption, reflection and refractive index. Other magnetic data and irradiation effects are included, as well as several bordering physical phenomena, such as piezoelectric properties, Debye temperature and thermal conductivity. Each property is compiled over the widest possible range of parameters from references obtained in a thorough literature search.

A crystallographic summary has been added.

This report has been reviewed and is approved for publication.

H. Thayne Johnson  
H. Thayne Johnson, Head  
Electronic Properties Information Center

John W. Atwood  
John W. Atwood  
Project Manager

## TABLE OF CONTENTS

	Page
Foreword . . . . .	iii
Abstract . . . . .	iv
Introduction . . . . .	1
Crystallography . . . . .	5
 Absorption . . . . .	9
Cross Sections . . . . .	17
Debye Temperature. . . . .	18
Dielectric Constant. . . . .	19
Effective Mass . . . . .	20
Electrical Conductivity. . . . .	21
Electrical Resistivity . . . . .	25
Electroacoustic Properties . . . . .	29
Electron Field Emission. . . . .	35
Electron Photoemission . . . . .	37
Electron Thermionic Emission . . . . .	38
Energy Bands . . . . .	39
Energy Gap . . . . .	45
Energy Levels . . . . .	46
Hall Coefficient . . . . .	50
Irradiation Properties . . . . .	54
Lifetime . . . . .	56
Magnetic Susceptibility. . . . .	58
Magnetoelectric Properties . . . . .	59
Mobility . . . . .	62
Photoelectronic Properties . . . . .	67
Photon Electroluminescence . . . . .	72
Photon Emissivity. . . . .	77
Photon Luminescence. . . . .	79
Photon Thermoluminescence . . . . .	85
Reflectivity . . . . .	86
Refractive Index . . . . .	89
Thermal Conductivity . . . . .	92
Thermoelectric Properties. . . . .	94
Work Function . . . . .	96
 References . . . . .	97
Publications of the Electronic Properties Information Center . . . . .	103

## INTRODUCTION

In June 1961, a program was initiated under the direction of the Air Force to collect, index and abstract the literature on the electrical and electronic properties of materials and to evaluate and compile the experimental data from that literature. Placed at Hughes Aircraft Company in Culver City, California, the program, now called the Electronic Properties Information Center, was originally intended to cover ten major categories of materials: Semiconductors, Insulators, Ceramics, Ferroelectrics, Metals, Ferrites, Ferromagnetics, Electro-luminescent Materials, Thermionic Emitters, and Superconductors.

During the first year, studies were completed on the Semiconductor and Insulator categories; and Ceramics was discontinued as a separate category and subsumed under the other nine. Vocabulary studies have now been completed on all categories, and retrospective documentation is virtually complete for Semiconductors and Insulators. A full index to the literature is maintained, and publications such as data sheets, summary reviews, glossaries, and thesauri are issued periodically. The use of the Center and these publications are available to anyone wishing information within the scope of the Center's objectives. A full list of publications to date appears at the end of this report.

The first step in the preparation of data sheets is the retrieval, by manual modified coordinate index, of all literature on the material to be compiled. Bibliographies are checked to ensure the inclusion of all relevant literature and the assembled articles are given to the specialist doing the evaluation and compilation.

Evaluation is confined to primary source data except when only secondary citations are available. If equally valid data are available from several

sources, all are given. Data are rejected when judged questionable because of faulty or dubious measurements, unknown sample composition, or if more reliable data are available from another source. Selection of data is based upon that which is judged most representative, precise, reliable and which covers the widest range of variables.

Pure silicon carbide is colourless, with a Mohs hardness over 9, almost equal to that of the diamonds that Acheson was attempting to synthesize when he created silicon carbide artificially in the arc furnace in 1891. The natural material, Moissanite, was discovered as small hexagonal plates in meteoric iron about 15 years later in 1904. Commercial silicon carbide is black, with a bluish or greenish iridescence, it is refractory to heat up to 1000°C, unreactive to chemical attack and melts at 2830°C. It is now produced in large quantities by the electric furnace method at Niagara Falls, and is used extensively as an abrasive, for drills and highly refractory bricks. In 1963, its capability as a CW diode laser was disclosed, [Ref. 17972].

A silicon carbide p-n junction operating at room temperature has an emission peak at  $4560\text{\AA}$  with a linewidth of less than  $5\text{\AA}$ , at threshold current densities of  $120 \text{ amps/cm}^2$ . This important discovery has renewed interest in the material. It is however, an extremely difficult and refractory material to handle and this fact is reflected in the quantity of published material. One hundred and eighty four papers in all, were available to represent work done since about 1955. The older data are well covered in Gmelins Handbuch, and it is only the new techniques of the past ten years that have made possible samples of predetermined quality. Of the one hundred and eighty four papers, seventy nine were used in these data sheets.

Within every property section, we have tried to include every possible parameter and range of experimental condition tested. All the available information on test and sample specifications is also given. All graphs and tabular data are extracted from the article and quoted without alteration of any kind.

In previous compilations, materials have been arranged to show firstly data on pure samples, and then by the various dopants. Silicon carbide however, has thus far, not been produced pure from the standpoint of either dopants or crystal type. This question will be discussed more fully in the section on crystallography. In any event, the arrangement is practically self-explanatory, the data being divided into the alpha and beta forms, single crystal and films, and the nitrogen-doped (n-type) or the aluminum-doped (p-type).

In tabular data, values are variously arranged. In some cases it is by dopant, in others by numerical value. On occasion, however, the values from one reference may be kept together for simple comparison.

The references, from which the data are drawn, are shown by reference numbers below each graph with the full bibliographic information at the end of the data sheets. The bibliography is referred to and listed in the order of entry into the Center (accession number). This provides a quick cross reference into the index used with the literature.

## CRYSTALLOGRAPHY

Silicon carbide is an unique material and a précis of its crystallographic characteristics is thoroughly covered by Gmelins Handbuch.<sup>1</sup> It is of the utmost importance to note, however, that the energy gap value changes with crystal structure by 1 ev; from 2.2 ev for the beta-silicon carbide to 3.12 ev for the alpha-silicon carbide (6H).<sup>2</sup> Such details, germane to the electronic properties of silicon carbide are given here.

Silicon carbide is both polymorphic and polytypic. The beta form is cubic and also called the low-temperature form. The alpha form is hexagonal and has 37 types of which 14 are hexagonal and 23 are rhombohedral. Many of these types are structurally equivalent in two directions with the same dimensions and lattice arrangement but dissimilar in the c-direction. Nomenclature is given according to Ramsdell, the chief investigator in this field, by H for hexagonal or R for rhombohedral. The number indicates the total number of silicon carbide layers in the (0001) direction which repeats one each of the unit crystal cells.

The three most generally occurring types are the 6H, often called (II modification), the 4H (III modification), both dihexagonal-dipyramidal and the 15R, rhombohedral, ditrigonal-pyramidal.<sup>1</sup> These occur together in varying percentages as a result of variations in growth conditions. These include changes in temperature, pressure, impurities present in the charge or excess of either silicon or carbon. Nitrogen is the major impurity and therefore pure material must be synthesized in an ambient inert gas (argon is used). Doping, with nitrogen, aluminum, boron or phosphorus is controlled. Twinning is common; there are three kinds, all on the basal plane and on three edges.

The beta form is body-centered cubic and very dense. Its yellow color is not due to any impurity, but to a shift of the fundamental absorption edge into the visible at  $\sim 4400 \text{ \AA}$ . Following are the four best lattice constant values:

$$a_o (\text{kX})$$

- 4.350 - very pure powder
- 4.352 - colourless crystal
- 4.349 - powder
- 4.348 - crystal

[1]

The alpha form has a tetrahedral lattice with silicon in the center and carbon at the four corners like silicon dioxide.

6H	$a_o (\text{kX})$	$c_o (\text{kX})$	4H	$a_o (\text{kX})$	$c_o (\text{kX})$
	3.075	15.088		3.0739	10.061
	3.073	15.068		3.076	10.046
	3.073	15.079		3.073	10.053
	3.076	15.070		3.08	10.09
	3.08	15.17		3.09	10.09
	3.09	15.17			

[1]

15R	H	$a_o (\text{kX})$	R	$a_o (\text{kX})$	$\alpha$
		3.076		12.78	$13^\circ 55'$
		3.073		12.703	$13^\circ 54'$
		3.073		12.691	$13^\circ 54.5'$
		3.09		12.78	$13^\circ 55'$
		3.08		12.775	$13^\circ 52'$

Ramsdell<sup>3</sup> in 1952 reported five hexagonal modifications including 8H, with an eight layer hexagonal unit cell,

$$a_o = 3.073 \text{ kX}$$

$$c_o = 20.106 \text{ kX}$$

In 1953<sup>4</sup> he reported 19H with a structure showing the zigzag sequence 22232323,

$$a_o = 3.073$$

$$c_o = 47.75 \text{ kX.}$$

In 1964 Chang-Lin Kuo<sup>5</sup> described two new polytypes:

$$417R, a_o = 3.0806 \text{ \AA}$$

$$c_o = 1050.7 \text{ \AA}$$

$$453R, a_o = 3.0806 \text{ \AA}$$


$$c_o = 1141.4 \text{ \AA}$$

These last references indicate the complexity and the continued interest in the crystallography of silicon carbide.

The commercial material ranges in color from yellow thru green and blue to


black. Silicon carbide is uniaxial positive and pleochroic.<sup>6</sup>

The phase diagram A is drawn from four points taken at 1 atm. pressure.<sup>7</sup>



B is a more recent phase diagram drawn from a large number of points at 35 atmos. pressure in argon over a range of 1408°C to 2900°C.<sup>8</sup>

Transformation from the beta to the alpha form is apparently by the vapour phase and not the solid, even at temperatures up to the melting point. The beta form is grown below 2000°C from the vapour and forms plates.<sup>9</sup> Silicon carbide crystals are not piezoelectric.




<sup>1</sup> GMELINS HANDBUCH DER ANORGANISCHEN CHEMIE; achte völlig neu bearbeitete Auflage. Silicium. Teil B. Weinheim, Verlag Chemie, GMBH, 1959.

<sup>2</sup> KNIPPENBERG, W.F. Growth Phenomena in Silicon Carbide. PHILIPS RES. REPTS., v. 18, no. 3, June 1963. p. 161-274. [Acces. no. 17402]

<sup>3</sup> RAMSDELL, L.S. and J.A. KOHN. Developments in Silicon Carbide Research. ACTA CRYST., v. 5, 1952. p. 215-224.

<sup>4</sup> RAMSDELL, L.S. and R.S. MITCHELL. A New Hexagonal Polymorph of Silicon Carbide, 19H. AMERICAN MINERALOGIST, v. 38, 1953. p. 56-59.

- 5 CHANG-LIN KUO. Two New Polytypes of Silicon Carbide 417R and 453R. WU LI HSUEH PAO, v. 20, 1964. p. 444-446.
- 6 DANA, J.D. The System of Mineralogy of James Dwight Dana and Edward Salisbury Dana. Yale University, 1837-1892. v.1, 7th ed. Entirely rewritten and greatly enlarged by PALACHE, C., et al. N.Y., Wiley, 1944. p. 123.
- 7 NOWOTNY, H., et al. MONATSH CHEM., v. 85, 1954, p. 255-272 as cited in CONSTITUTION OF BINARY ALLOYS, by HANSEN, M., N.Y., Mc Graw-Hill, 1958.
- 8 SCACE, R.I. and G.A. SLACK. The Silicon Carbide and Germanium Carbide Phase Diagrams. In: CONF. ON SILICON CARBIDE, BOSTON, 1959. SILICON CARBIDE, A HIGH TEMPERATURE SEMICONDUCTOR, PROC., ed. by O'CONNOR, J.R. and J. SMILTENS. N.Y., Symposium Pub. Div., Pergamon Press, 1960. p. 366-371. [Acc. no. 17418]
- 9 GORIN, S.N. and A.A. PLETYUSHKIN. Structural Characteristics of Cubic Silicon Carbide Crystals Grown from the Vapor Phase. IZV. AKAD. NAUK SSSR., SER. FIZ., v. 28, 1964. p. 1310-1315.




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### ABSORPTION

Absorption as a function of wavelength for pure, colourless, single crystal, alpha-silicon carbide (6H), at several temperatures.




[Ref. 4434]




[Ref. 4434]


Intrinsic absorption as a function of wavelength at 300°K, for single crystal, alpha-silicon carbide (6H), cut parallel to c-axis. Above 5 ev points are calculated from reflectivity data.



[Ref. 17419]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA



Absorption as a function of wavelength for single crystal, n-type, alpha-silicon carbide, (6H). Curves calculated from transmission data, at 300°K. An N-doped inhomogeneous green crystal is used,  $\rho \sim 1 \text{ ohm}\cdot\text{cm}$ . The 3 curves indicate varying carrier concentrations.


[Ref. 628]



Absorption as a function of wavelength for single crystal, alpha-silicon carbide at 77°K,  $E_{\perp c}$ -axis.

The two curves indicate the absorption edge difference between the (6H) and (4H) polytype.

[Ref. 8792]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE


### ABSORPTION

Absorption as a function of wavelength for single crystal, n-type, alpha-silicon carbide, nitrogen-doped.

carrier concentration	$\rho$ (ohm-cm)
15 - $4.5 \times 10^{17}$ /cc	0.2
31 - $40 \times 10^{17}$	0.48
33 - $200 \times 10^{17}$	0.0085




[Ref. 16397]



Absorption as a function of wavelength for single crystal, alpha-silicon carbide, (6H), at four temperatures.

[Ref. 13404]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### ABSORPTION


Absorption as a function of wavelength for single crystal, alpha silicon carbide at 300°K.

p-type colorless,  $\rho = 10^4$  ohm-cm,  $n \sim 10^{14}/\text{cc.}$

n-type green,  $\rho = 10^2$  ohm-cm.




[Ref. 2863]



Absorption as a function of wavelength for single crystal alpha silicon carbide, (6H), at 300°K. Blue crystals are p-type, aluminum-doped,  $\rho = 50$  ohm-cm, green is n-type,  $\rho = 3$  ohm-cm.

[Ref. 2514]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### ABSORPTION

Infra-red transmission of clear, single crystal, n-type, alpha silicon carbide, (6H), at 300°K.




[Ref. 17415]



Infra-red transmission of clear and light green, nitrogen-doped, single crystal, n-type, alpha silicon carbide, (6H), at 300°K.

---- clear, 0.07 mm thick  
— green, 0.007 mm thick.

[Ref. 17415]





PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### ABSORPTION

Absorption as a function of wavelength for single crystal, alpha and beta-silicon carbide, at 300°K. The alpha form is (6H), polytype.



[Ref. 787]


Absorption as a function of wavelength for single crystal, n-type, silicon carbide. 1, 2, and 3 are alpha-form, commercial grade.

$$\begin{aligned} 1 - n &= 6.7 \times 10^{18} / \text{cc} \\ 2 - n &= 2.5 \times 10^{18} / \text{cc} \\ 3 - n &= 9.5 \times 10^{16} / \text{cc} \end{aligned}$$

4 is pure beta-form,  $n = 1.3 \times 10^{17} / \text{cc}$ .

The wave number power on the curves shows the absorption slope.

[Ref. 17233]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE


### ABSORPTION

Transmission as a function of wavelength for single crystal, n-type, alpha-silicon carbide at various temperatures.




[Ref. 3607]

Transmission as a function of wavelength for single crystal, n-type, alpha-silicon carbide at 300°K. 132 is pure, argon grown. The other samples show increasing amounts of the nitrogen dopant.




[Ref. 3607]

Transmission as a function of wavelength for single crystal, p-type, alpha-silicon carbide at 300°K. 115 is pure, argon grown, 98, 201, and 96 show increasing amounts of the aluminum dopant.




[Ref. 3607]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

### SILICON CARBIDE




[Ref. 18056]

Transmission as a function of wavelength for single crystal, n-type, beta-silicon carbide at temperatures from 295-700°K.  $n \sim 10^{17}/\text{cc}$ ,  $\rho_{500\text{K}} \sim 0.1 \text{ ohm}\cdot\text{cm}$ .



Transmission as a function of wavelength for polycrystalline beta-silicon carbide film at 300°K.

[Ref. 627]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### CROSS SECTIONS

Symbol	Value	Sample	Test Method	Temperature	Ref.
$\sigma$	$\sim 10^{-23} \text{ cm}^2$	Al-doped, single crystal, $\alpha$ -silicon carbide p-n junction	electroluminescence	300°K	368
calculated for intrinsic recombination					




Impurity level densities, and recombination cross-sections for both radiative and non-radiative transitions at 77°K. derived from a study of the electroluminescence of single crystal, alpha-silicon carbide p-n junctions between 77-830°K, 0.04 to 2.5 microns and 100 microamps/cm<sup>2</sup> to 3 amps/cm<sup>2</sup>.

Q - the Quasi-Fermi level

$E_F$  - the Fermi level

$\sigma_r$  - average cross-section for hole-electron radiative recombination

$\sigma_n$  - average cross-section for hole-electron non-radiative recombination




## SILICON CARBIDE

### DEBYE TEMPERATURE $\theta$

Value	Sample	Test Method	Temperature	Ref.
1200°K	high purity, single crystal	calc. from thermal conductivity meas.	>300°K	17406
913°K		calc. from specific heat measurement	53-73°K	*Gmelin
949°K			73.5°K	
1192°K			700-900°K	

\* GMELINS HANDBUCH DER ANORGANISCHEN CHEMIE; achte völlig neu bearbeitete Auflage.  
Silicium. Teil B. Weinheim, Verlag Chemie, GMBH, 1959. p. 820.



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### DIELECTRIC CONSTANT

Symbol	Value	Sample	Test Method	Temperature	Ref.
$\epsilon_0$	10.62	27**	single crystal, pure	1 kc	20°K
	10.38	17		5	
	10.26	5		32	
	10.23	3		100	
	10.99	49		1	77°K
	10.69	29		5	
	10.42	14		32	
	10.34	8		100	3410
$\epsilon_0$	10.0 ± 0.1	single crystal, $\alpha$ , $\rho > 1 \text{ ohm-cm}$	IR optical, 1-25 $\mu$ $\lambda > 12.6\mu$	300°K	628
$\epsilon_\infty$	6.7		$\lambda < 12.6\mu$		628
$\epsilon_\infty$	6.7	epitaxial single crystal film	IR optical measurement at 1-15 $\mu$		627
	50-200	powder	up to 30 kc		*Gmelin

\*\* This column shows  $\tan \delta \times 10^{-3}$  values for the sample under the given conditions.

\*GMELINS HANDBUCH DER ANORGANISCHEN CHEMIE; achte völlig neu bearbeitete Auflage.  
Silicium. Teil B. Weinheim, Verlag Chemie, GMBH, 1959. p. 829.




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### EFFECTIVE MASS

Symbol	Value	Sample	Test Method	Temperature	Ref.
$m^*$	2.5 (calc.)	single crystal, p-, n-type, $n = 8 \times 10^{19}/\text{cc}$	elec. conductivity and Hall measurement		2419
$m_n$	0.6	single crystal, n-, and p- type	"	300°K	3608
$m_p$	1.2-2	single crystal, $\alpha$ , N-, B- or Al-doped	"	"	3608
$m_p^*$	~1.0	single crystal, p-type, $\alpha$ ,	mobility meas. from Hall cond. data	77-1500°K	8783
$m_n$	0.72	Al- and B-doped			
$m_p$	3.5				8783

\* - density of states Effective Mass



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE


### ELECTRICAL CONDUCTIVITY

Electrical conductivity as a function of temperature for single crystal, alpha-silicon carbide.


1 - n-type, N-doped,  $n \sim 10^{17}/\text{cc.}$ , (6H)

2 - n-type, N-doped,  $n \sim 10^{19}/\text{cc.}$ , (6H)

3 - n-type, Al-doped,  $n = 4 \times 10^{19}/\text{cc.}$ , (6H) and (15R).




[Ref. 17725]



Electrical conductivity as a function of temperature for p-type, single crystal, alpha-silicon carbide.

$n = 2 \times 10^{17} \text{ to } > 10^{20}/\text{cc.}$

[Ref. 18406]





PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### ELECTRICAL CONDUCTIVITY

Electrical conductivity as a function of temperature for single crystal, alpha-silicon carbide, black crystals, with varied cross-section and carrier concentration.




[Ref. 6080]

Current voltage curves of single crystal, alpha-silicon carbide at 300°K.

	$\rho$ ohm-cm
1 - p-type, B-doped,	670,000
2 - " "	53,000
3 - " "	11,000
4 - undoped	5,300

[Ref. 5908]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### ELECTRICAL CONDUCTIVITY

Electrical conductivity as a function of temperature for single crystal, alpha and beta-silicon carbide, pale yellow to green. Samples from 1 to 5 have varied cross-section and show increase in impurity by colour change from pale yellow to dark green.




[Ref. 6080]



Electrical conductivity as a function of temperature for n-type, fairly pure, beta-silicon carbide.


[Ref. 17725]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### ELECTRICAL CONDUCTIVITY



Electrical conductivity as a function of temperature for beta-silicon carbide, both single crystal, and polycrystalline.

[Ref. 17416]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE



### ELECTRICAL RESISTIVITY

Resistivity as a function of temperature for n-type, single crystal, alpha-silicon carbide.

a) is grown in pure argon, no dopants, the other curves show increasing amounts of nitrogen,

n from  $10^{17}$  to  $5 \times 10^{19}/\text{cc.}$

d) and e) also have aluminum and boron impurities.




[Ref. 3608]

Resistivity as a function of temperature for single crystal, alpha-silicon carbide.

p) and s) are grown in pure argon  
q) and r) in argon and boron  
t) in argon + aluminum.

n varies from  $10^{17}$  to  $10^{18}/\text{cc.}$

[Ref. 3608]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

SILICON CARBIDE


ELECTRICAL RESISTIVITY

1)  $n = 6.4 \times 10^{16}/\text{cc.}$




Resistivity as a function of temperature for n-type, single crystal,  
alpha-silicon carbide, fairly pure, slightly N-doped.

[Ref. 17973]



2)  $n = 3 \times 10^{17}/\text{cc.}$

[Ref. 17973]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### ELECTRICAL RESISTIVITY

Resistivity as a function of temperature for n-type, single crystal, nitrogen-doped, alpha-silicon carbide, (6H).

#### carrier concentration


6 -	1. $\times 10^{17}$ /cc
15 -	4.5
30 -	30.
31 -	40.
33 -	200.



[Ref. 16397]

Approximate Resistivity (ohm-cm)	Dopant in Single crystal, β-SiC (ppm)	Crystal Type	Color	Temperature
0.5	60 B	p	green	300°K
$10^{-1}$	200 Al	p	blue-green	
10	< 10 Al	p	yellow-green	
$10^3$	no Al detected	n	light yellow	
$10^3$	no B detected	n	light yellow	

[Ref. 17725]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### ELECTRICAL RESISTIVITY


Log electrical resistivity as a function of electric field for pure, alpha-silicon carbide grains.

A - grains heated 2.5 hours at 1950°C in argon

N<sub>2</sub> - grains heated 2.5 hours at 1950°C in nitrogen gas.



[Ref. 17403]




Log electrical resistivity as a function of field for commercial silicon carbide grains.

1 to 4 are for alpha-SiC of varied impurity

5 is beta-silicon carbide grain.

[Ref. 17403]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### ELECTROACOUSTIC PROPERTIES

Pure, and nitrogen-doped, n-type, single crystal,  $\alpha$ -SiC, (6H), at 6°K.  $n = 10^{15}$  to  $10^{17}$ /cc. Phonon energies in ev for various  $k$  vectors from luminescent data.

Phonon branch	$k_c = 2\pi/c$	$k_c = 4\pi/c$	$k_c = 6\pi/c$	
TA	.0335 .0363	.0392 .0403	.044 .0463	
LA	.0506 .0535	.0670 .069	.077	
TO	.0978	.0956	.0947	
LO	.107	.1055	.1042	[Ref. 6505]

Phonon branch	Value	Sample	Test Method	Temperature
LO	0.12 ev	n-type, N-doped, $\alpha$ -,	reflectivity data	300°K
TO	0.095			[Ref. 3607]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### ELECTROACOUSTIC PROPERTIES

Phonon energies for single crystal, n-type, nitrogen-doped,  $\alpha$  and  $\beta$ -silicon carbide at 6°K.


Phonon branch	$\beta$	15R	$\frac{\alpha}{\beta}$	6H	Ref.
TA	.0463 ev	.0463 ev		.0463 ev	17405
LA	.0794	.0782		.077	
TO	.0944	.0946		.0947	
LO	.1028	.1037		.1042	17405
TA		.0344		.0335	13156
TA		.0350		.0363	
TA		.0393		.0392	
TA		.0397		.0403	
TA		.0432		.044	
TA		.0463		.0463	
LA		.0513		.0506	
LA		.0519		.0535	
LA		.0692		.067	
LA		.0702		.0690	
LA		.0782		.077	
TO		.0946		.0947	
TO		.0953		.0956	
TO		.0957		.0978	
TO		.0971			
LO		.1037		.1042	
LO		.1063		.1055	
LO		.1069		.107	13156



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### ELECTROACOUSTIC PROPERTIES




[Ref. 17974]

Luminescence spectrum at 6°K of four-particle nitrogen-exciton complexes in single crystal, alpha-silicon carbide, (4H).  $P_0$  and  $Q_0$  are zero-phonon lines.



Luminescence spectrum of pure, single crystal, alpha-silicon carbide, (6H), at 6°K,  $n = 10^{15}/\text{cc}$ . The two additional intrinsic lines ( $I_{44.0}$  &  $I_{46.3}$ ) are due to recombination of free excitons.

[Ref. 6505]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### ELECTROACOUSTIC PROPERTIES

Complete four-particle nitrogen-exciton luminescence spectrum at 6°K, for n-type, single crystal, alpha-silicon carbide, (15R). The four phonon-free lines are marked. Exciton energy gap = 2.98 ev.




[Ref. 13156]



One of the four series of luminescence lines shown in the P series of A. The zero of energy has been placed at P<sub>0</sub>, so that the energies of emitted phonons may be read directly.


[Ref. 13156]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### ELECTROACOUSTIC PROPERTIES




Samples are pure, single crystal, alpha-silicon carbide, (6H), at 6°K.  
 $n = 10^{15} / \text{cc.}$

— Acoustic phonon lines

[Ref. 6505]


The phonon energy in ev represents the displacement of the energy from that of the phonon free line  $P_0$ . Polarization is parallel or normal to the c-axis.

Optical phonon lines —



Phonon energy (mev) ( $P_0 = 0$ )

[Ref. 6505]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE


### ELECTROACOUSTIC PROPERTIES

Absorption edge of single crystal, n-type, beta-silicon carbide, at 4.2°K. Arrows indicate possible phonon emission. Exciton energy gap is 2.39 ev.




[Ref. 6505]

The luminescence spectrum of four-particle nitrogen-exciton complexes in single crystal, beta-silicon carbide at 6°K. The phonon branch energies may be read directly from the (mev) scale with 0 = phonon-free line.




[Ref. 17405]

Absorption edges of pure, n-type, single crystal, alpha-silicon carbide, (6H), in polarized light at 77°K.  
 $n = 10^{15}/\text{cc.}$



[Ref. 17405]




• PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

• SILICON CARBIDE


ELECTRON-FIELD EMISSION

Electron emission as a function of field in single crystal, alpha-silicon carbide p-n junction, formed by boron diffusion, (curves 1 to 5).

Voltage-current characteristics for the same sample are shown by curves 1' to 5'.



[Ref. 17414]




Electron emission as a function of field for single crystal, alpha-silicon carbide p-n junction at two temperatures.

1 - 293°K

2 - 673°K


[Ref. 17414]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE


### ELECTRON-FIELD EMISSION



Electron emission as a function of field for single crystal,  
alpha-silicon carbide p-n junction.

- 1 - 293°K
- 2 - 473°K
- 3 - 553°K
- 4 - 663°K
- 5 - 773°K

[Ref. 14663]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### ELECTRON PHOTOEMISSION

Electron photoemission as a function of wavelength for single crystal, (yellow color), beta-silicon carbide at 300°K.




[Ref. 787]



Electron photoemission as a function of wavelength in n-type, single crystal, (green color), alpha-silicon carbide at 300°K.  $\rho = 0.6$  ohm-cm. The surfaces were variously treated by ion bombardment alone, and with annealing, as well as exposure to oxygen.

- A - ion bombardment
- B - ion bombardment + 1000°C anneal at 2 hrs.
- C - ion bombardment + 1000°C anneal at 20 hrs.
- D - oxygen exposure


[Ref. 7134]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### ELECTRON THERMIONIC-EMISSION



Electron thermionic emission in single crystal, alpha-silicon carbide, (commercial grade). Data at increasing temperatures are not reversible and fresh samples are required for each run.

[Ref. 7152]



• PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


• SILICON CARBIDE

ENERGY BANDS

Symbol	Value (ev/°K)	Sample (single crystal)	Test Measurement	Temperature	Ref.
$dEg/dT$	$-5.8 \pm 0.3 \times 10^{-4}$	n-type, $\alpha$ -, $n = 10^{17}/\text{cc}$ $\rho \sim 0.1 \text{ ohm}\cdot\text{cm}$	transmission at .885 to 428 $\mu$	295-700°K	18056
$dEg/dT$	$-5 \times 10^{-4}$	n-type, $\alpha$ -, (6H), N-doped	$10^4$ oe, elec. resistivity, Hall	200-800°K	16397
	$-1.2 \times 10^{-4}$ at the 200 per cm absorp. band	$n \sim 10^{17}/\text{cc}$ (001) oriented	meas. at 10 oe, also optical absorp. at .35 to 2.5 $\mu$		
$dEg/dT$	$-3.3 \times 10^{-4}$	$\alpha$ -,	transmission and photoelectric	>300°K	17417
$dEg/dT$	$-3$ to $-6 \times 10^{-4}$	n-, and p-type, $\alpha$ -.	photoconductivity $\lambda = 0.6$ to 5.5 ev	80-800°K	10994
	$-3$ to $-4 \times 10^{-4}$	"	p-n junction photo- effect	"	
$dEg/dT$	$-3.3$ to $3.4 \times 10^{-4}$	n-type, $\alpha$ -, (6H), (001) oriented,	absorption	100°K, 293°K, 4596 & 500°K	
$dI/dT$	$-3.8 \pm 0.6 \times 10^{-4}$	$\rho_{300K} = 7.5 \text{ ohm}\cdot\text{cm}$	photoconductivity		4596
$E_{dc}$	11.5 ev	p-type, $\alpha$ -, (6H), pure, (argon atmos.) Cl in argon, Al, O <sub>2</sub> , N impurity in all		300-1300°K	8783
$E_{dv}$	13				

$E_{dc}$  = deformation potential of conduction band

$E_{dv}$  = deformation potential of valence band




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

SILICON CARBIDE

ENERGY BANDS


Symbol	Value (ev/ $^{\circ}$ K)	Sample (single crystal)	Test Measurement	Temperature	Ref.
$E_1 - E_2$	.0048 ev	spin orbit splitting of valence band	photolum.	6 $^{\circ}$ K	6505
$k\theta$ 1 phonon energy	0.09 ev	indirect transition in an $\alpha$ -, (6H) sample	transmission and photoelectric	77-717 $^{\circ}$ K	17417



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE


## **ENERGY BANDS**




Energy band structure of beta silicon carbide crystal obtained by OPW-calculation.  
 The numbers at the top side of the figure represent those of the OPW-terms involved.  
 [Ref. 2348]

Ry	ev
.2	2.7
.4	5.4
.6	8.1
.8	10.8
1.	13.5
1.2	16.2
1.4	18.9
1.6	21.6
1.8	24.3

Band structure of silicon carbide. The computed values for the electronic states at the symmetry points  $\Gamma$ , L, and X are indicated by circles. The lines indicate the expected band profiles in the directions  $\Delta$  and  $\Delta'$ .



[Ref. 14587]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### ENERGY BANDS

Effect on energy gap of crystalline, poly-type. Two samples of alpha silicon carbide, (6H) and (4H), are measured at 77°K, E normal to c-axis.




[Ref. 8792]



Observed splittings of the three valence bands in silicon carbide. The small spin-orbit interaction splits  $E_1$  and  $E_2$ , and a much larger crystal field interaction splits off  $E_3$ .


[Ref. 6505]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### ENERGY BANDS




Shift in energy gap as a function of temperature at constant current density for lightly coloured p- and n-type single crystal alpha silicon carbide.

[Ref. 2514]



Shift in energy gap as a function of current density for lightly coloured p- and n-type single crystal alpha silicon carbide.

[Ref. 2514]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### ENERGY BANDS

Energy gap as a function of temperature for pure, colorless, alpha-silicon carbide.




[Ref. 3607]



Shift in energy gap as a function of temperature for alpha-silicon carbide.

[Ref. 17417]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### ENERGY GAP

Symbol	Value (ev)	Sample (single crystal)	Test Measurement	Temperature	Ref.
$E_g$	3.12	$\alpha$ -, (6H)	optical absorp.	300°K	787
	2.62	pure, $\beta$ -,	"	"	787
	2.86	$\alpha$ -, (6H)	"	"	17419
	2.2	$\beta$ -,	"	"	17419
	$3.1 \pm 0.2$	n-type, $\alpha$ -,	conductivity, from 950-2000°K	0°K	17455
$\sim 3$		pure, colorless, $\alpha$ -,	optical absorp.	300°K	3607
$\sim 2.8$		yellow, $\beta$ -,	"	"	3607
	2.986	n-type, N-doped, $\alpha$ -, (15R)	luminescence	6°K	13156
	2.86	$\alpha$ -,	optical	300°K	17417
	$2.83 \pm 0.1$	p-n junction	radiation recomb.	300°K	7333
	2.8	n-type, green, $\rho = 10^2$ ohm-cm p-type, colorless, $\rho = 10^4$ ohm-cm	transmission at .22-.1 micron	300°K	2863




## SILICON CARBIDE

### ENERGY LEVELS

#### Explanation of Symbols used in Energy Levels Table

**VB** - distance above valence band in ev  
**CB** - distance below conduction band in ev  
 **$E_C$**  - conduction band edge  
 **$E_V$**  - valence band edge  
 **$E_F$**  - Fermi level  
 **$E_D$**  - donor ionization energy level  
 **$E_A$**  - acceptor ionization energy level  
 **$E_{Gx}$**  - exciton energy gap  
 **$E_{peak}$**  - photon energy at emission peak

Symbol	Value (ev)	Dopant	Sample (single crystal)	Test Measurement	Temperature	Ref.
$E_D$	0.02	N	n-type, $\beta$ -,	electrical conductivity		17725
$E_D$	0.09	N	n-type, $\alpha$ -,	"		17725
$E_D$	0.086	N	n-type, $\alpha$ -, (6H) $n = 10^{17}/\text{cc}$	Hall & resistivity meas. at $10^4$ oe	100-1000°K	16397
	0.063		$\rho = .425 \text{ ohm-cm}$			
	0.23		$\rho = 0.2 \text{ ohm-cm}$			16397
			$\rho = 0.048 \text{ ohm-cm}$			
$E_D$	0.17	N	n-type, $\alpha$ -, (6H)	photoluminescence	77°K	11725
	0.20	N	"	"	"	
	0.23	N	"	"	"	11725



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### ENERGY LEVELS

Symbol	Value (ev)	Dopant	Sample (single crystals)	Test Measurements	Temperature	Ref.
$E_A$	0.21	Al & 1 Mev electrons	n-type, $\rho \sim 0.5 \text{ ohm-cm}$ $n \sim 10^{18}/\text{cc}$	Hall measurements		15717
	0.22		$n \sim 10^{18}$	radiation recombination		
	0.23		$n \sim 7 \times 10^{17}$	Hall measurements		
	0.25		$n \sim 7 \times 10^{17}$	radiation recombination		15717
$E_D$	0.47	fast neutron flux	n-type	resistivity measurement	300°K	*
$E_A$	0.24	$10^{17}/\text{cm}^2$	p-type			
$E_F$	0.63		p-n junction, $\alpha$ -,	calculated from	673°K	7333
$E_F$	0.52		$n \sim 8 \times 10^{17}/\text{cc}$	radiation recomb. & resistivity meas.	300°K	
$E_F$	0.47 to 0.54		$\rho = 10^5 \text{ ohm-cm}$		300°K	7333

Symbol		Sample, Resistivity and Colour	Test Measurements	Temperature	Ref.
$E_1$	$E_2$	n-type, $\alpha$ -, single transparent crystals	electrical conductivity		6080
1.57		$10^{13} \text{ ohm-cm}$		>1300°K	
0.441		$10^3$		1100°K	
0.304		10		625°K	
0.263	0.147	1		565°K	
0.198	0.097	.3		480°K	
0.2	0.5	p-type, $\alpha$ -, opaque 1 ohm-cm		~1000°K	6080

\* CENTRE D' ETUDE DE L' ENERGIE NUCLEAIRE. MOL, BELGIUM. Solid State Neutron Detector.  
QR No. 6, Jan. 1 - Mar. 31, 1962. EURAEC-306. Contract No. 079-61-10RDB. 1962.



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### ENERGY LEVELS


Symbol	Value (ev)	Dopant	Sample (single crystal)	Test Measurement	Temperature	Ref.
$E_D$	0.14	N	n-type, $\alpha$ -, (15R)	optical absorption and luminescence	60K	13156
	0.16	N				13156
	0.20	N				
$E_D$	0.6	N	n-type, $\alpha$ -, $n \sim 10^{18}/\text{cc}$	Hall and conductivity meas. $n \sim 10^{17}/\text{cc}$	3608	3608
	0.8 <sub>CB</sub>					3608

$E_{Gx} - E_{\text{peak}}$	$E_{Gx}$	$E_{\text{peak}}$	Emission Color	Sample	Test	
				B- & N-doped, $\alpha$ -, powders	Measurement Temp.	Ref.
0.95 ev	3.263 ev	2.317 ev	green	(4H)	photo-	300°K 17404
0.89	3.023	2.137	yellow	(6H)	luminescence	
0.91	3.01	2.101	orange	(33R)	at	
0.94	2.986	2.049	orange-red	(15R)	.365 microns	
0.88	2.86	1.983	red	(21R)		
0.91	2.80	(1.89)		(8H)		
0.91	2.390	(1.48)		(3C)		17404

$E_A$	0.27 <sub>VB</sub>	Al	p-type, $\alpha$ -,	Hall & electrical resistivity	300-1300°K	8783
$E_A$	0.39 <sub>VB</sub>		"		"	8783

$E_A$	0.275 <sub>VB</sub>	Al	p-type, $\alpha$ -, $n < 10^{18}/\text{cc}$	Hall & conductivity measurement		3608
-------	---------------------	----	---	---------------------------------	--	------

$E_D$	0.15	N	n-type, $\alpha$ -,	glow curve data	106°K	3607
$E_D$	0.20	Al	p-type, $\alpha$ -,	"	233°K	3607
$E_A$	0.085 <sub>CB</sub>	N	n-type, $\alpha$ -,	fluorescence	77°K	3607
$E_A$	0.27 <sub>VB</sub>		p-type, $\alpha$ -,	"	"	3607




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### ENERGY LEVELS


Energy level diagram showing the relation of the three nitrogen donor levels [A, B, and C] to that obtained by the hydrogenic approximation. The difference between 0.13 ev and a donor level may be taken as a rough measure of the valley-orbit splitting for that donor.



[Ref. 11725]




Energy level diagram for electroluminescence in silicon carbide. [Ref. 2899]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### HALL COEFFICIENT




[Ref. 5464]

Hall coefficient as a function of temperature for pure, n-type, single crystal, alpha-silicon carbide.

$1 - n \sim 10^{14}/\text{cc}$	$\rho_{300K} = 40 \text{ ohm}\cdot\text{cm}$
2 - $n_c$	.2
3 - $a_{si}$	.1
4 - $n_g$	.04
5 - $n \sim 10^{16}/\text{cc}$	.1

Dotted lines indicate no experimental points.




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

### SILICON CARBIDE


#### HALL COEFFICIENT

Hall coefficient as a function of temperature for p-type, single crystal, alpha-silicon carbide, (prepared in argon, argon + boron chloride and argon + aluminum chloride).

- p - undoped       $n \sim 10^{17}/\text{cc}$
- q - B-doped       $n = 2.3 \times 10^{17}$
- r - "               $n = 9.5 \times 10^{17}$
- s - Al-doped       $n = 10^{18}$




[Ref. 3608]



[Ref. 16397]

Hall coefficient as a function of temperature for n-type, single crystal, alpha-silicon carbide, (6H).


- |                                   |                          |
|-----------------------------------|--------------------------|
| 6 - $\rho = .425 \text{ ohm-cm.}$ | $n = 10^{17}/\text{cc.}$ |
| 15 - .2                           | $4.5 \times 10^{17}$     |
| 30 - .053                         | $30 \times 10^{17}$      |
| 31 - .048                         | $40 \times 10^{17}$      |
| 33 - .0085                        | $200 \times 10^{17}$     |



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### HALL COEFFICIENT




Hall coefficient as a function of temperature for single crystal, alpha-silicon carbide.

A - n-type, green


o -  $\rho = .12 \text{ ohm-cm}$  at  $480^{\circ}\text{K}$   
x -  $\rho = 1.0 \text{ ohm-cm}$  at  $620^{\circ}\text{K}$   
• -  $\rho = .5 \text{ ohm-cm}$  at  $570^{\circ}\text{K}$

B - p-type, black

$\rho_{1000\text{K}} \sim 0.05 \text{ ohm-cm}$ .



[Ref. 5990]




Hall coefficient as a function of temperature for n-type, alpha-silicon carbide, (prepared in argon, argon + nitrogen and for [h] argon, nitrogen and aluminum chloride).

a - undoped	$n = 3.6 \times 10^{17}/\text{cc.}$
c - N-, Al-, B-,	$10^{17}$
d -	$10^{18}$
e -	$10^{19}$
f - N-doped	$n = 5.0 \times 10^{19}$
g - "	$n = 3.4 \times 10^{19}$
h - N-, Al-doped	$n = 3.0 \times 10^{18}$

The dotted line is a theoretical curve.

[Ref. 3608]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### HALL COEFFICIENT


$$n = 5.6 \times 10^{17} / \text{cc.}$$

$$\rho_{290K} = .222 \text{ ohm-cm.}$$




Hall coefficient as a function of temperature  
for n-type, single crystal, alpha-silicon carbide.

[Ref. 17973]




[Ref. 17973]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### IRRADIATION PROPERTIES



Photoluminescence as a function of wavelength for p-type, single crystal, alpha-silicon carbide at 300°K. The samples were irradiated by  $5 \times 10^{11}$  neutrons/cm<sup>2</sup> sec.


A - characteristic fluorescence of aluminum-doped sample

B - after 10 minutes irradiation

[Ref. 18349]

According to their original quality, silicon carbide diodes are affected by a fast neutron radiation flux of  $10^{14}/\text{cm}^2$  to  $10^{16}$  or  $10^{17}/\text{cm}^2$ . \*


\* CENTRE D' ETUDE DE L' ENERGIE NUCLEAIRE, BRUSSELS. Solid State Detector for Neutrons. QR No. 2, Jan. - Mar. 1961. EURAEC-107. 1961.



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER - HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

• SILICON CARBIDE

IRRADIATION PROPERTIES



Current-voltage characteristics in the forward (a) and reverse (b) directions for unirradiated (1) and irradiated (2) single crystal, alpha-silicon carbide p-n junctions. The original material was n-type,  $n \sim 5 \times 10^{17}/\text{cc}$ . Radiation used is:


- I -  $\gamma$ -rays
- II -  $\beta$ -rays
- III -  $\gamma$ -rays + neutrons

No change in current-voltage characteristics but a junction photoeffect occurs.  
[Ref. 19624]

A fast neutron flux of  $2.2 \times 10^{17}/\text{cm}^2$  changes p-type, single crystal,  $\alpha$ -silicon carbide to n-type. n-Type remains unaffected by a  $3.8 \times 10^{16}/\text{cm}^2$  flux. Optical transmission is only slightly affected by  $nvt_f = 10^{16}/\text{cm}^2$  from .4 to 2.5 microns. 1 ohm-cm, n-type,  $\alpha$ -silicon carbide, single crystal after  $10^{16}/\text{cm}^2$  neutron irradiation has 100 ohm-cm resistivity.

Mobility	Sample	Irradiation	Temperature	Ref.
$15 \text{ cm}^2/\text{v sec}$	single crystal, p-type	non-irradiated	$500^\circ\text{K}$	*
$50 \text{ cm}^2/\text{v sec}$	single crystal, n-type	$nvt_f = 10^{16}/\text{cm}^2$	$500^\circ\text{K}$	

\* CENTRE D' ETUDE DE L' ENERGIE NUCLEAIRE. MOL, BELGIUM. Solid State Neutron Detector. QR No. 6, Jan. 1 - Mar. 31, 1962. EURAEC-306. Contract No. 079-61-10RDB. 1962.




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### LIFETIME

Symbol	Value (μsec)	Sample (single crystal)	Test Method	Temperature	Ref.
$\tau_p$	80	p-n junction, α-,	recomb. radiation	133°K	2152
$\tau_p$	1.15	"	"	300°K	2152
$\tau_p$	~ 30	n-type, α-,	photoconductivity	300°K	11441
$\tau_p$	1.	p-n junction, α-,	recomb. radiation	300°K	7867
$\tau_p$	30	p-type, boron-doped, α-, $\rho = 11000 \text{ ohm-cm}$	current voltage	300°K	5908
$\tau_p$	.3	n-type, pure, argon grown, white, α-, $\rho = 5300 \text{ ohm-cm}$	"	"	5908
$\tau_p$	.008 to .02	n-type, nitrogen-doped, α-, $\rho = .2 \text{ to } 10 \text{ ohm-cm}$	photoconductivity & electroluminescence	300°K	10533
$\tau_p$	0.01	p-type, aluminum-doped, α-, to 90000 ohm-cm	"	300°K	10533
$\tau_p$	.01 to 1.0	n-type, aluminum-doped, α-, $n \sim 10^{18} / \text{cc}$ , $\rho = .5 \text{ ohm-cm}$	recomb. radiation after 1 Mev electron irradiation	200-350°K	15717
$\tau_n$	3	p-type, boron-doped, α-, $\rho = 11000 \text{ ohm-cm}$	current voltage	300°K	5908
$\tau_n$	< 0.5	p-n junction, α-,	electroluminescence	300°K	17421
$\tau_n$	~ .4 .1 .004 .009	n-type, α-, " " p-type, α-,	"	300°K	7805
$\tau_n$	.01	p-n junction, n-type, Al-doped $n_n \sim 10^{18} / \text{cc}$	electroluminescence	300°K	368
$\tau_n$	.01 to .05	n- and p-type, aluminum-doped, β-,		300°K	17725
$\tau$	<3	β-, single crystal & polycrystalline	electrical		17416




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### LIFETIME

Lifetime as a function of current density for single crystal, alpha-silicon carbide, (p-n junctions). The points give the hole lifetime and the curves give, at the same temperatures, the relative number of photons per unit current, i.e., relative efficiency, at 6 microns. The curves are normalized to bring out the correlation with the hole lifetimes.




[Ref. 368]




Lifetime as a function of temperature for n-type, single crystal, alpha-silicon carbide; photoconductivity measurements.

[Ref. 11441]

Lifetime as a function of frequency for single crystal, alpha-silicon carbide at 300°K. 1, 2 and 4 are n-type, 3 is p-type. → indicate τ at 35% of maximum value.



[Ref. 7805]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### MAGNETIC SUSCEPTIBILITY

Symbol	Value	Sample (single crystal)	Test Method	Temperature	Ref.
(mean value)					
$\chi$	$-12.8 \times 10^{-6}$ /gm mol [ $0.316 \times 10^{-6}$ /cgs units]	green, $\alpha$ -,	4640-6160 oe	300°K	13757
$\chi_{\perp}$	$-13.1 \times 10^{-6}$ /gm mol [- $0.326 \times 10^{-6}$ /cgs units]				13757
$\chi_{\perp}$	$-5.4$ to $8.2 \times 10^{-6}$ /gm mol	black, $\alpha$ -,			13757
$\chi$	$-0.319 \times 10^{-6}$ /cgs units				7359
$\chi_{\parallel} \chi_{\perp}$	(magnetic anisotropy) $0.82 \times 10^{-6}$ /gm mol [ $0.02 \times 10^{-6}$ /cgs units]		3560-4250 oe	300°K	13757



Magnetic susceptibility is shown in both molar and cgs units.



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER - HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

SILICON CARBIDE

MAGNETOELECTRIC PROPERTIES



Magnetic field  $H$ , (kcps)

Magnetoresistance as a function of magnetic field for fairly pure, (slightly N-doped), n-type, alpha-silicon carbide.

I)  $n = 3 \times 10^{17} / \text{cc}$


- 1 -  $4.23^\circ\text{K}$
- 2 -  $3.23^\circ\text{K}$
- 3 -  $2.08^\circ\text{K}$
- 4 -  $1.55^\circ\text{K}$
- 5 -  $1.43^\circ\text{K}$

II)  $n = 6.4 \times 10^{16} / \text{cc}$

- 1 -  $4.21^\circ\text{K}$
- 2 -  $3.10^\circ\text{K}$
- 3 -  $2.54^\circ\text{K}$
- 4 -  $2.01^\circ\text{K}$
- 5 -  $1.63^\circ\text{K}$

o and x are data taken with different probes.

[Ref. 17973]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### MAGNETOELECTRIC PROPERTIES

Transverse magnetoresistance coefficient as a function of magnetic field in n-type, single crystal, alpha-silicon carbide at 77°K, H parallel to c-axis.




[Ref. 11132]



Transverse magnetoresistance coefficient as  $\vec{H}$  is rotated with respect to  $\vec{J}$  in n-type, single crystal, alpha-silicon carbide, at 77°K.  $H = 3900$  oe.

[Ref. 11132]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### MAGNETOELECTRIC PROPERTIES

Magnetoresistance as a function of angle for n-type, single crystal, alpha-silicon carbide at 77°K and 3900 oe.




[Ref. 11132]



Magnetoresistance as a function of  $\theta$ , angle between magnetic field and current for n-type, single crystal, alpha-silicon carbide at 4.22°K.

- 1 - 6.1 kc
- 2 - 11.6 kc
- 3 - 15.7 kc

[Ref. 17073]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### MOBILITY



Symbol	Value		Sample (single crystal)	Temperature	Ref.	
		<u>n /cc</u>	<u>p (ohm-cm)</u>			
$\mu$	>2000 400	$\sim 10^{14}$	10.	n-type, pure, $\alpha$ -, (6H)	77°K 300°K	5464
				↓		
	40 38	$\sim 10^{16}$	.3		77°K 300°K	5464
				↓		
$\mu$	360 160 142 90 37	$2 \times 10^{17}$ 1 30 40 200	.425 .2 .053 .048 .0085	n-type, N-doped, $\alpha$ -, (6H)	293°K	16397
				↓		
$\mu$	26	422.	p-type	photo. meas. at	300°K	409
$\mu_n$	2100 3265 4670	$1.67 \times 10^{16}$ $1.18 \times 10^{15}$ $1.38 \times 10^{15}$	.179 .163 .971	n-type, very pure, $\beta$ -,	300°K	17725
				↓		
$\mu_n$	150 62	$1.3 \times 10^{17}$ $3.6 \times 10^{17}$		n-type, N-doped, $\alpha$ -,	300°K 500°K	17233 17233
				↓		
$\mu_n$	32		.00185	n-type, light green, $\beta$ -,	300°K	17416
				↓		
$\mu_n$ $\mu_p$	220 48	$< 10^{15}$		n-type, pure, $\alpha$ -, (argon grown)	300°K	8783 8783



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### MOBILITY




[Ref. 5990]

Mobility as a function of temperature for single crystal, alpha-silicon carbide.

A - p-type, black,  $\rho_{1000K} \sim .05 \text{ ohm-cm.}$


B - n-type, green,  $\rho = \begin{cases} 0.12 & \text{at } 480^\circ\text{K} \\ 1.0 & \text{at } 620^\circ\text{K} \\ 0.5 & \text{at } 570^\circ\text{K} \end{cases}$



Mobility as a function of temperature for very pure, n-type, single crystal, alpha-silicon carbide, (6H).

	$n / \text{cc}$	$\rho_{300K} \text{ ohm-cm}$
A	$\sim 10^{14}$	40.
B		2.
C		.1
D		.04
E	$10^{16}$	.1

[Ref. 5464]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE


### MOBILITY

Mobility as a function of temperature for p-type, single crystal, alpha-silicon carbide, prepared in argon, argon + boron chloride, and argon + aluminum chloride.

p - undoped	$n \sim 10^{17}/\text{cc}$
q - Al-doped {	{ $n = 2.4 \times 10^{18}$
- B-doped {	{ $n = 2.3 \times 10^{17}$
r - Al-doped {	{ $n = 3.7 \times 10^{18}$
- B-doped {	{ $n = 9.5 \times 10^{17}$
s - Al-doped	$n = 10^{18}$




[Ref. 3608]



Mobility as a function of temperature for n-type, single crystal, alpha-silicon carbide, prepared in argon, or argon + nitrogen.

a - no dopant	$n_n = 3.6 \times 10^{17}/\text{cc}$
b - N-, Al-, B-, n	$\sim 10^{17}$
c - N-, Al-, B-, n	$\sim 10^{18}$
d - N-, Al-, B-, n	$= 3 \times 10^{18}$
e - N-, Al-, B-, n	$= 10^{19}$
f - N-doped,	$n = 5 \times 10^{19}$
g - N-doped	$n = 3.4 \times 10^{19}$



[Ref. 3608]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE


### MOBILITY



Mobility as a function of temperature for p-type, single crystal, alpha-silicon carbide, (6H). Principal dopants are aluminum, boron, and chlorine. Nitrogen is always present. Dashed lines are calculated for - 1) polar, 2) acoustical, and 3) piezoelectric scattering. The solid line is the sum of the two and the dots show experimental points.

- argon grown (fairly pure)
- + { oxygen, oxygen and chlorine
- ^ { aluminum
- ▲ { boron
- o chlorine-doped

[Ref. 8783]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE


### MOBILITY

Mobility as a function of temperature for n-type, N-doped, single crystal, alpha-silicon carbide.

$\rho_{300K}$ ohm-cm	$n / \text{cc}$
1 - 0.425	$10^{17}$
2 - 0.2	$10^{17}$
3 - 0.53	$3 \times 10^{18}$
4 - 0.48	$4 \times 10^{18}$
5 - 0.0085	$2 \times 10^{19}$




[Ref. 16397]



Electron mobility as a function of temperature for n-type, single crystal, alpha-silicon carbide, (111) oriented.

$n / \text{cc}$	$\rho_{290K}$ ohm-cm
1) o $5.7 \times 10^{18}$	.0175
2) x	.0174
3) ▽ $5.6 \times 10^{17}$	.222


[Ref. 17973]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### PHOTOELECTRONIC PROPERTIES




[Ref. 4596]

Photoconductivity as a function of wavelength for n-type, single crystal, alpha-silicon carbide, (6H), (001) oriented.

$$\rho_{300K} = 7.5 \text{ ohm-cm.}$$

- 1 - 100°K
- 2 - 293°K
- 3 - 500°K




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE


### PHOTOELECTRONIC PROPERTIES

Photoconductivity and electrical resistivity as a function of temperature for n-type, single crystal, alpha-silicon carbide.

- 1 - electrical resistivity
- 2 - photoconductivity at 1.03 microns
- 3 - photoconductivity at 0.32 microns




[Ref. 10994]



Photoconductivity as a function of wavelength for n-type, single crystal, alpha-silicon carbide.

- 1 - 125°K
- 2 - 180°K
- 3 - 200°K
- 4 - 230°K
- 5 - 260°K
- 6 - 300°K

[Ref. 10994]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE


### PHOTOELECTRONIC PROPERTIES

Photoconductivity and electrical resistivity as a function of temperature for p-type, single crystal, alpha-silicon carbide.

- 1 - electrical resistivity
- 2 - photoconductivity at 1.05 microns
- 3 - photoconductivity at 0.35 microns




[Ref. 10994]



Photoconductivity as a function of wavelength for p-type, single crystal, alpha-silicon carbide at 80°K and 400°K.

[Ref. 10994]





PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### PHOTOELECTRONIC PROPERTIES

Photoconductivity (1) and photovoltage (2) for n-type, single crystal, alpha-silicon carbide at 300°K. Photovoltage normalized to 1. Photoconductivity placed only for comparison, without units.




Photovoltage as a function of wavelength for p-n junction, single crystal alpha-silicon carbide at various temperatures.


[Ref. 10994]

Photovoltage as a function of wavelength for p-type, single crystal, alpha-silicon carbide at several temperatures. Photovoltage normalized to 1.

[Ref. 7741]



[Ref. 7867]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### PHOTOELECTRONIC PROPERTIES

Current-Voltage curve of an n-type, single crystal, alpha-silicon carbide photoelement at light intensities from .32 to 7.5 mW/cm<sup>2</sup>.




[Ref. 7741]



Photovoltage and short circuit current density as a function of temperature for p-n junction, single crystal, alpha-silicon carbide at constant illumination.

— short circuit density  
--- photovoltage


[Ref. 7867]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### PHOTON ELECTROLUMINESCENCE



Stimulated emission in a forward-biased p-n junction of alpha-silicon carbide. Emission peak at .456 microns has a linewidth <0.005 microns. Continuous operation at 300°K around 120 amps/cm<sup>2</sup>.

[Ref. 17972]





PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### PHOTON ELECTROLUMINESCENCE

Photo electroluminescence as a function of wavelength for single crystal, alpha-silicon carbide p-n junction at 500°K, and several current intensities.


a is the same curve on both graphs on a different scale.



[Ref. 18406]

Photo electroluminescence as a function of wavelength for single crystal, alpha-silicon carbide p-n junction at several temperatures and 100 amps/cm<sup>2</sup>.

[Ref. 18406]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE


### PHOTON ELECTROLUMINESCENCE

Electroluminescence as a function of wavelength in single crystal, alpha-silicon carbide p-n junctions of several polytypes at 300°K.  $\rho < .3 \text{ ohm-cm}$ . The 3C curve is for n-type, beta-silicon carbide,  $\rho < 0.4 \text{ ohm-cm}$ . Current density was 0.05 to 0.1 amp/cm<sup>2</sup>.

Photon electroluminescence is measured in photons/unit time and energy.




[Ref. 18818]



Electroluminescence as a function of DC current in fairly pure, light green, single crystal, alpha-silicon carbide p-n junction at 300°K.

The curve starts at .065 milliamp.


[Ref. 2152]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

SILICON CARBIDE

PHOTON ELECTROLUMINESCENCE




Photon electroluminescence in single crystal, alpha-silicon carbide p-n junction. Various impurities are present.

$$n \sim 10^{18}/\text{cc.}, \rho = .2 \text{ ohm-cm.}$$

- 1 - 130°K, 1 amp/cm<sup>2</sup>
- 2 - 400°K, 1 amp/cm<sup>2</sup>
- 3 - 700°K, 1 amp/cm<sup>2</sup>
- 4 - 700°K, 100 amps/cm<sup>2</sup>

[Ref. 17457]

Photon electroluminescence is measured in photons/unit time and energy.




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### PHOTON ELECTROLUMINESCENCE

Normalized photon electroluminescence as a function of wavelength in n-type, single crystal, pale green, alpha-silicon carbide at 300°K. The current varies from 1.0 to 7.5 microamps.




Electroluminescence as a function of wavelength for single crystal, alpha-silicon carbide p-n junction, at several temperatures and 1 amp/cm<sup>2</sup>. Curves are normalized at .6 microns.




[Ref. 2152]

Photon and electroluminescence as a function of wavelength for single crystal, alpha-silicon carbide p-n junction at 77°K. Increase in excitation by a factor of 10 is indicated in electroluminescent spectra by shift to higher wavelength, but similar increase in UV excitation has no effect on photoluminescent spectrum.

[Ref. 368]




[Ref. 368]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### PHOTON EMISSIVITY




[Ref. 2217]

Spectral emissivity of Globar heating element as a function of wavelength at four temperatures.

### Spectral Emissivity

Value	Sample	Temperature	Ref.
0.85%	sintered silicon carbide rods at 1.6 microns	1243°K	17724
0.93%	polycrystalline commercial silicon carbide	1500°F	1956




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### PHOTON EMISSIVITY

Spectral emissivity as a function of wavelength for sintered silicon carbide rods at 1243°K. Spectral emissivity is normalized to the standard black body base.




[Ref. 17724]



Spectral emissivity as a function of wavelength for commercially pure, fine grained silicon carbide at 2 temperatures.

[Ref. 17412]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### PHOTON LUMINESCENCE

Photon luminescence as a function of wavelength for alpha-silicon carbide powder, B-, and N-doped, at 300°K. Curves indicate the polytype from x-ray determinations.




[Ref. 17404]



Photon luminescence as a function of wavelength for single crystal, alpha-silicon carbide, (6H), at 4°K, (001) oriented. The subscripts indicate the level number.



[Ref. 11690]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### PHOTON LUMINESCENCE



[Ref. 11690]

Photon luminescence for single crystal, alpha-silicon carbide, (6H), at 4°K and 77°K, giving fine structure of the peaks in I.



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### PHOTON LUMINESCENCE


Photon luminescence as a function of temperature for single crystal, beta-silicon carbide p-n junction, (nitrogen-boron).  $\rho = 0.08\text{-}0.4 \text{ ohm}\cdot\text{cm}$ .

1, 2 - photoluminescence for UV irradiation

1', 2', - quenching curves whose slope equal thermal quenching activation energy 0.29-0.3 ev.




[Ref. 18818]



Photon luminescence as a function of temperature for single crystal, alpha-silicon carbide (6H) and (8H) p-n junction, (nitrogen-boron).  $\rho = 0.05 \text{ to } 0.3 \text{ ohm}\cdot\text{cm}$ .

1' is quenching curve whose slope is  $\sim 0.35$  ev.

[Ref. 18818]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE


### PHOTON LUMINESCENCE

Photon luminescence as a function of wavelength for single crystal, alpha-silicon carbide at 63°K.

- a - n-type, N-doped, white,  $n \sim 10^{18}/\text{cc}$
- b - n-type, N-doped, green,  $n = 2.7 \times 10^{18}$
- c - p-type, Al-doped, light blue,  $n \sim 10^{18}$



[Ref. 3607]



Photon luminescence as a function of wavelength for single crystal, alpha-silicon carbide, (6H), at several temperatures.


a) transparent colorless crystal,

- 1 - 423°K
- 2 - 123°K
- 3 - 90°K

b) black crystal,

- 1 - 423°K
- 2 - 333°K
- 3 - 273°K
- 4 - 194°K
- 5 - 90°K


[Ref. 13404]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

SILICON CARBIDE

PHOTON LUMINESCENCE



curves 1, 2, 3

Photon luminescence as a function of temperature for n-type, single crystal, alpha-silicon carbide, (6H), nitrogen-doped.


$$n = 10^{17} \text{ to } 5 \times 10^{18} / \text{cc}, \rho_{300\text{K}} = 0.02 \text{ to } 1 \text{ ohm-cm.}$$

curves 4, 5, 6

Photon luminescence as a function of temperature for single crystal, alpha-silicon carbide p-n junctions.

Curves 4 and 5 are for the (6H) polytype  
Curve 6 is for the (4H) polytype.

[Ref. 17730]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### PHOTON LUMINESCENCE

Photon luminescence as a function of temperature for n-type, single crystal, alpha-silicon carbide, (6H).

1 - blue luminescence

2 - orange




[Ref. 13404]

Photoluminescence maxima, dopant, and electrical resistivity for single crystal, beta-silicon carbide.

Crystal Type	Dopant	Resistivity (ohm-cm)	Luminescence at 77°K Color	Luminescence at 300°K Color
n	Al	$10^3$	brilliant orange	yellow
p-n	Al		brilliant pink	none
p	Al	10	brilliant pink	none
n	+N <sub>2</sub> + Al	$10^{-1}$	bright orange	dull red
n	Al, Mo + N <sub>2</sub>	$10^{-2}$	bright pink	yellow
n	Al, + N <sub>2</sub>	$10^{-1}$	orange	dull red
n	Mg	1 - 10	pink	none
n		1 - 10	orange	green, yellow, red
n		4 - 10	dull orange	yellow, red, green
p	Al	$10^{-1}$	very dull green, pink, yellow	none
n	Ca	1 - 10	very dull red	dull red
n	B	$10^3$	very dull orange	bright yellow, red & green


[Ref. 17725]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

SILICON CARBIDE

PHOTON THERMOLUMINESCENCE




Photon thermoluminescence as a function of temperature for single crystal, alpha-silicon carbide. Excitation at 83°K and .365 microns.

A - p-type, Al-doped, light blue,  $n \sim 10^{18}/\text{cc}$ .

B - n-type, nitrogen-doped, white,  $n \sim 10^{18}/\text{cc}$ .

[Ref. 3607]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE


### REFLECTIVITY

Reflectivity as a function of wavelength for pure, single crystal, alpha-silicon carbide at 300°K.


$E \parallel$  to the c-axis

$n_e \perp$  to the c-axis

$n_w \parallel$  to the c-axis




[Ref. 3607]




[Ref. 628]

Reflectivity as a function of wavelength for single crystal, alpha-silicon carbide at 300°K. Below 3 ev these values are calculated from direct measurements of index of refraction in [Ref. 13873].



[Ref. 17419]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


### SILICON CARBIDE

#### REFLECTIVITY

Reflectivity as a function of wavelength for single crystal, alpha-silicon carbide, (6H), at 300°K. E is normal to the c-axis.




[Ref. 628]



Reflectivity as a function of wavelength for polycrystalline, beta-silicon carbide films at 300°K.

- - 0.06 microns thick
- - 0.12 microns thick


[Ref. 627]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


SILICON CARBIDE

REFLECTIVITY



[Ref. 627]

Reflectivity as a function of wavelength for polycrystalline,  
beta-silicon carbide film, 0.06 microns thick.



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### REFRACTIVE INDEX

Symbol	Value (at 300°K)	Sample (single crystal)	Test Method (wavelength)	Ref.
n	~ 2.63	β-, yellow to olive green	.6708μ	13873
ε				
2.673	2.633	α-, (001), green-black	.6708μ	*Larsen
2.697	2.654	(Moissanite)	.5895μ	
2.721	2.675		.5351μ	
2.6889	2.6475	α-, (6H), light green	.5895μ	13873
2.6892	2.6468	α-, (15R), pale green	.5895μ	13873
2.654	2.616	α-, pale green	.755μ	**Gmelin


.6708μ is Li

.5895μ is Na

.5351μ is Tl

\* Larsen, E.S., and H. Berman. The Microscopic Determination of the Nonopaque Minerals. U.S.G.P.O., Washington, 1934. p. 77

\*\* GMELINS HANDBUCH DER ANORGANISCHEN CHEMIE; achte völlig neu bearbeitete Auflage. Silicium. Teil B. Weinheim, Verlag Chemie, GMBH, 1959. p. 827.




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


### SILICON CARBIDE

#### REFRACTIVE INDEX

Index of refraction of single crystal, alpha-silicon carbide, (6H), at 300°K. Below 3 ev the values are taken from [Ref. 13873].




[Ref. 17419]




Refractive index as a function of wavelength for pure, single crystal, alpha-silicon carbide at 300°K. (Calculated from reflectivity data.)

The extinction coefficient, i.e., the imaginary part of the index of refraction, of single crystal, alpha-silicon carbide, (6H), at 300°K.

[Ref. 17419]



[Ref. 13404]




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA


## SILICON CARBIDE

### REFRACTIVE INDEX

The theoretically calculated optical constants as a function of wavelength for single crystal, n-type, alpha-silicon carbide, (6H).




[Ref. 628]



Refractive index of ordinary  $n_e$  rays and extraordinary  $n_w$  rays as a function of wavelength in fairly pure, single crystal, alpha-silicon carbide at 300°K.  $n_e - n_w$  is the birefringence curve.\*

\*Gmelin, p. 827



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### THERMAL CONDUCTIVITY

Thermal conductivity as a function of temperature for single crystal, alpha-silicon carbide of varied purity.

A - n-type, N-doped, colorless, (6H),


$n \sim 10^{17}/\text{cc.}$ ,  $\rho_{300K} \sim 10 \text{ ohm-cm.}$

B - n-type, N- & Al-doped, light green, (6H),

$n \sim 10^{19}/\text{cc.}$ ,  $\rho_{300K} = 2 \text{ ohm-cm.}$

C - p-type, Al-doped, dark blue, (6H & 15R),

$n = 4 \times 10^{19}/\text{cc.}$ ,  $\rho_{300K} \sim .6 \text{ ohm-cm.}$



[Ref. 17406]


Thermal conductivity of sample A. Slightly N-doped.

Temperature °K	Thermal Conductivity w/cm deg.	Ref.
50	52	17406
70	43	
100	28	
150	15	
200	9.5	
300	4.9	
500	2.4*	
1000	1.1*	
1200	0.9*	17406
1478	.157**	1956
343	2.05***	17374

\* extrapolated

\*\* commercial polycrystalline, alpha-silicon carbide

\*\*\* polycrystalline




PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE


### THERMAL CONDUCTIVITY

Thermal conductivity as a function of temperature for single crystal, alpha-silicon carbide, (6H), and N-doped, polycrystalline, beta-silicon carbide.

$$n < 10^{17}/\text{cc.}$$




[Ref. 19150]



Thermal conductivity as a function of temperature for commercial, poly-crystalline, alpha-silicon carbide.

[Ref. 17411]





PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### THERMOELECTRIC PROPERTIES

Thermoelectric emf as a function of temperature for n-type, single crystal, yellow, beta-silicon carbide.  
 $\rho \sim 1$  to 100 ohm-cm.



[Ref. 17416]

Thermoelectric emf as a function of temperature for single crystal, alpha-silicon carbide with resistivities to  $10^4$  ohm-cm.


- 1 - n-type,  $n = 5.6 \times 10^{16}/\text{cc}$
- 2 - n-type,  $n = 2.7 \times 10^{17}$
- 4 - n-type,  $n = 2.7 \times 10^{17}$
- 5 - p-type,  $n = 2.0 \times 10^{18}$

[Ref. 5896]


Thermal emf as a function of temperature for single crystal, alpha-silicon carbide.

A - n-type, N-doped, green

B - p-type, Al-doped, black




[Ref. 6031]



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### THERMOELECTRIC PROPERTIES




Thermoelectric emf as a function of temperature for two silicon carbide samples.

A - Single crystal, alpha-silicon carbide,  $\rho = 45 \text{ ohm-cm}$ , colorless, becomes p-type above 680°K.

B - Single crystal, n-type, alpha-silicon carbide,  $\rho = 0.026 \text{ ohm-cm}$ , dark green, remains n-type with heating.

[Ref. 19560]

Symbol	Value ( $\mu\text{v}/^\circ\text{K}$ )	Sample	Ref.
Q	20-50	polycrystalline commercial material, $\rho \sim 0.05 \text{ ohm-cm}$	3974
	200 ± 10%	polycrystalline, $\beta$ -SiC rods	17416
	-106	n-type, single crystal, yellow, $\beta$ -, $\rho = 0.1 \text{ to } 100 \text{ ohm-cm}$	17416



PREPARED BY ELECTRONIC PROPERTIES INFORMATION CENTER • HUGHES AIRCRAFT COMPANY, CULVER CITY, CALIFORNIA

## SILICON CARBIDE

### WORK FUNCTION

Symbol	Value (ev)	Sample (single crystal)	Test Method	Temperature	Ref.
$\phi$	4.62	impure, p-type, $\alpha$ -, $\rho = 0.3 \text{ ohm-cm.}$ , black	photoelectric emission	300°K	7134
$\phi$	4.55	impure, p-type, $\alpha$ -, $\rho = 0.6 \text{ ohm-cm.}$ , green	"		7134
$\phi$	$\sim 4$	impure, $\alpha$ -,	electron thermionic emission	1000-1700°K	7152
$\sim 3 \text{ ev}$ (2.3 to 4)		impure, n- and p-type, black green to light green yellow		300-800°K	2468
Electron affinity $\psi$ $\sim 4 \text{ ev}$		$\beta^-$	photoelectric data	300°K	787
Photoelectric threshold $\sim 7 \text{ ev}$		$\beta^-$	"	"	787

## REFERENCES

- 368 LYLE, P. and W.J. CHOYKE. Impurity Bands and Electroluminescence in SiC p-n Junctions. J. OF APPLIED PHYS., v. 30, no. 2, Feb. 1959. p. 236-248.
- 409 VAN DER MAESEN, F. Determination of Numbers of Injected Holes and Electrons in Semiconductors. PHILIPS RES. REPTS., v. 15, no. 2, Apr. 1960. p. 107-119.
- 627 SPITZER, W.G., et al. Infrared Properties of Cubic Silicon Carbide Films. PHYS. REV., v. 113, no. 1, Jan. 1, 1959. p. 133-136.
- 628 SPITZER, W.G., et al. Infrared Properties of Hexagonal Silicon Carbide. PHYS. REV., v. 113, no. 1, Jan. 1, 1959. p. 127-132.
- 787 PHILLIP, H.R. Intrinsic Optical Absorption in Single-Crystal Silicon Carbide. PHYS. REV., v. 111, no. 2, July 15, 1958. p. 440-441.
- 953 PRIMAK, W., et al. Radiation Damage in Diamond and Silicon Carbide. PHYS. REV., v. 103, no. 5, Sept. 1, 1956. p. 1184-1192.
- 1956 BROWN, R.W. Taking the Black Magic Out of High-Temperature Nonmetallics. CHEM. ENG., v. 65, Apr. 21, 1958. p. 146-147.
- 2152 LEHOVEC, K., et al. Light Emission Produced by Current Injected into a Green Silicon-Carbide Crystal. PHYS. REV., v. 89, no. 1, Jan. 1, 1953. p. 20-25.
- 2217 STEWART, J.E. and J.C. RICHMOND. Infrared Emission Spectrum of Silicon Carbide Heating Elements. NAT. BUREAU OF STANDARDS, J. OF RES., v. 59, no. 6, Dec. 1957. p. 405-409.
- 2348 KOBAYASI, S. Calculation of the Energy Band Structure of the Beta-SiC Crystal by the Orthogonalized Plane Wave Method. PHYS. SOC. OF JAPAN, J., v. 13, no. 3, Mar. 1958. p. 261-268.
- 2419 LEHOVEC, K. and H. KEDESDY. Graphical Determination of the Fermi Level in a Simple Impurity Semiconductor. J. OF APPLIED PHYS., v. 22, no. 1, Jan. 1951. p. 65-67.
- 2468 HOLM, E. Contribution to the Theory of the Silicon Carbide Contact. J. OF APPLIED PHYS., v. 23, no. 5, May 1952. p. 509-517.
- 2514 RUECKER, D. Zur Elektrolumineszenz des Siliziumkarbids. The Electroluminescence of Silicon Carbide. ZEITSCHRIFT FUER ANGEWANDTE PHYS., v. 10, no. 6, 1958. p. 254-263.
- 2863 NAMBA, M. Optical Properties of Silicon Carbide. PHYS. AND CHEM. OF SOLIDS, v. 2, no. 4, 1957. p. 339-340.
- 2899 SZIGETI, G. Ueber die Durch Gleichstrom Angeregte Elektrolumineszenz von Siliziumkarbidkristallen. The D.C. Activated Electroluminescence of Silicon Carbide Crystals. ACTA PHYSICA HUNGARICA, v. 4, no. 1, 1954. p. 65-77.
- 3394 DALVEN, R. Absorption Edge in Beta-Silicon Carbide. PHYS. AND CHEM. OF SOLIDS., v. 13, no. 1-2, May 1960. p. 163-164.

- 3607 LELY, J.A. and F.A. KROEGER. Optical Properties of Pure and Doped SiC. In: SEMICONDUCTORS AND PHOSPHORS. HALBLEITER UND PHOSPHORE. PROC. OF INTERNAT. COLLOQUIUM-PARTENKIRCHEN. Ed. by SCHOEN, M. and H. WELKER. N.Y., Intersci. Pub., Inc. 1958. p. 514-524.
- 3608 LELY, J.A. and F.A. KROEGER. Electrical Properties of Hexagonal SiC Doped with N, B, or Al. In: SEMICONDUCTORS AND PHOSPHORS. HALBLEITER UND PHOSPHORE. PROC. OF INTERNAT. COLLOQUIUM-PARTENKIRCHEN. Ed. by SCHOEN, M. and H. WELKER. N.Y., Intersci. Pub., Inc., '58. p. 525-533.
- 3974 NATIONAL CARBON CO., INC. Thermoelectric Materials, by THIELKE, N.R. Bimonthly progress rept. no. 2, Mar. 28-May 28, 1959. June 15, 1959. Contract NObs-77066. ASTIA AD-229 057.
- 4434 GROTH, R. and E. KAUER. Absorption freier Ladungstraeger in alpha-SiC-Kristallen. Absorption by Free Charge Carriers in alpha-SiC Crystals. PHYSICA STATUS SOLIDI, v. 1, no. 5, 1961. p. 445-450.
- 4596 POROZHNIKOVA, G.N. and G.F. KHOIUYANOV. Photoconductivity in alpha-Silicon Carbide. SOVIET PHYS. - SOLID STATE, v. 3, no. 12, June 1962. p. 2657-2661.
- 5464 WESTINGHOUSE ELECTRIC CORP. Research in the Preparation of Hyperpure Single Crystal Silicon Carbide, by HAMILTON, D.R., et al. Final Rept. Feb. 1957-June 1959. Apr. 1960. AFCRL TR 60-368. Contract AF 19 604 2174. ASTIA AD-250 119.
- 5896 LOMAKINA, G.A. and Yu. A. VODAKOV. Effect of Phonon Drag in alpha-SiC Crystals. SOVIET PHYS. - SOLID STATE, v. 4, no. 3, Sept. 1962. p. 603-604.
- 5908 OZAROW, V. and R.E. HYSELL. Space-Charge-Limited Currents in Single-Crystal Silicon Carbide. J. OF APPLIED PHYS., v. 33, no. 10, Oct. 1962. p. 3013-3015.
- 5990 BUSCH, G. and H. LABHART. Ueber den Mechanismus der elektrischen Leitfaehigkeit des Siliziumkarbids. On the Mechanism of the Electrical Conductivity in Silicon Carbide. HELVETICA PHYSICA ACTA, v. 19, no. 6-7, 1946. p. 463-492.
- 6031 BUSCH, G. et al. Thermospannungen des Siliziumkarbids gegen Kupfer und Platin. Thermo-Voltages of Silicon Carbide with Copper or Platinum. HELVETICA PHYSICA ACTA, v. 20, no. 6, 1947. p. 461-463.
- 6080 BUSCH, G. Die elektrische Leitfaehigkeit des Siliziumkarbids. Electrical Conductivity of Silicon Carbide. HELVETICA PHYSICA ACTA, v. 19, no. 3, 1946. p. 167-188.
- 6397 WOOLEY, J.C. and B. RAY. Effects of Solid Solution of  $In_2Te_3$  with  $A^{II}B^{VI}$  Tellurides. PHYS. AND CHEM. OF SOLIDS, v. 15, no. 1-2, Aug. 1960. p. 27-32.
- 6505 CHOYKE, W.J. and L. PATRICK. Exciton Recombination Radiation and Phonon Spectrum of 6H SiC. PHYS. REV., v. 127, no. 6, Sept. 15, 1962. p. 1868-1877.
- 7134 DILLON, J.A., JR., et al. Some Surface Properties of Silicon-Carbide Crystals. J. OF APPLIED PHYS., v. 30, no. 5, May 1959. p. 675-679.

- 7152 BRAUN, A. and G. BUSCH. Versuche zur Messung der thermischen Elektronen-emission von Graphit, Silizium und Siliziumkarbid. Investigations in Measurements of Thermal Electron Emission of Graphite, Silicon and Silicon Carbide. HELVETICA PHYSICA ACTA, v. 20, no. 1, Feb. 15, 1947. p. 33-66.
- 7333 PATRICK, L. Structure and Characteristics of Silicon Carbide Light-Emitting Junctions. J. OF APPLIED PHYS., v. 28, no. 7, July 1957. p. 765-776.
- 7359 AIGRAIN, P. and M. BALKANSKI. Selected Constants Relative to Semi-Conductors. Oxford, N.Y., Pergamon Press, 1961.
- 7741 THIESSEN, K. and G. JUNGK. Photo-EMK bei Stoerstellen-und Grundgitteranregung im SiC. Photo-EMF for Defect Points and Basic Lattice Excitation in SiC. PHYSICA STATUS SOLIDI, v. 2, no. 4, 1962. p. 473-478.
- 7805 HARMAN, G.G. and R.L. RAYBOLD. Measurement of Minority Carrier Lifetime in SiC by a Novel Electroluminescent Method. J. OF APPLIED PHYS., v. 32, no. 6, June 1961. p. 1168-1169.
- 7867 KHOLUYANOV, G.F. Photoelectric Properties of Alloy p-n Junctions in Silicon Carbide. SOVIET PHYS. - SOLID STATE, v. 2, no. 8, Feb. 1961. p. 1722-1726.
- 8783 VAN DAAL, H.J., et al. On the Electronic Conduction of alpha-SiC Crystals between 300 and 1500°K. J. OF PHYS. AND CHEM. OF SOLIDS, v. 24, Jan. 1963. p. 109-127.
- 8792 CHOYKE, W.J. and L. PATRICK. Exciton and Interband Absorption in SiC. In: INTERNAT. CONF. ON SEMICONDUCTOR PHYS., PROC., PRAGUE, 1960. N.Y. Acad. Press, 1961. p. 432-434.
- 10533 KHOLUYANOV, G.F. Photoconductivity Relaxation and the Charge Carrier Lifetime in Silicon Carbide. SOVIET PHYS. - SOLID STATE, v. 4, no. 11, May 1963. p. 2322-2326.
- 10994 JUNGK, G., et al. Stationare Photoleitung und p-n-Photoeffekt in SiC. Stationary Photoconductivity and p-n Photoeffect in SiC. PHYSICA STATUS SOLIDI, v. 3, no. 4, 1963. p. 735-743.
- 11132 MASS. INST. OF TECH. LINCOLN LAB. Solid State Research. QPR, Aug. 1, 1957. ASTIA AD-151 261.
- 11441 THIESSEN, K., et al. Zur Kinetik der Photoleitung in SiC. The Kinetics of Photoconductivity in SiC. PHYSICA STATUS SOLIDI, v. 3, no. 3, 1963. p. 529-534.
- 11690 CHOYKE, W.J., et al. Polarized Edge Emission of SiC. PHYS. REV., v. 117, no. 6, Mar. 15, 1960. p. 1430-1438.
- 11938 SZIGETI, G. Short Lecture Given During the Session on Electroluminescence. BRITISH J. OF APPLIED PHYS., v. 6, supp. no. 4, 1955. p. s56.
- 13156 PATRICK, L., et al. Optical Properties of 15R Silicon Carbide Luminescence of Nitrogen-Exciton Complexes, and Interband Absorption. PHYS. REV., v. 132, no. 5, Dec. 1, 1963. p. 2023-2031.

- 13404 GORBAN, I.S. and S.N. RUDKO. Optical Properties of Silicon Carbide Crystals. SOVIET PHYS. - SOLID STATE, v. 5, no. 5, Nov. 1963. p. 995-998.
- 13757 SIGAMONY, A. The Magnetic Susceptibility and Anisotropy of Carborundum. INDIAN ACAD. OF SCI., PROC., A, v. 19, 1944. p. 377-380.
- 13873 THIBAULT, N.W. Morphological and Structural Crystallography and Optical Properties of Silicon Carbide. AMERICAN MINERALOGIST, v. 29, no. 9-10, Sept.-Oct., 1944. p. 327-362.
- 14587 BASSANI, F. and M. YOSHIMINE. Electronic Band Structure of Group IV Elements and of III-V Compounds. PHYS. REV., v. 130, no. 1, Apr. 1, 1963. p. 20-33.
- 14663 STEPANOV, G.V., et al. Emission of Hot Electrons from Natural p-n Junctions in Silicon Carbide Crystals. SOVIET PHYS. - SOLID STATE, v. 3, no. 6, Dec. 1961. p. 1280-1283.
- 15717 VAN DER DOES DE BYE, J.A.W. Transient Recombination in Silicon Carbide. PHILIPS RES. REPTS., v. 17, no. 5, Oct. 1962. p. 418-430.
- 16397 VIOLINA, G.N., et al. Optical Absorption and Electrical Properties of n-Type alpha-Silicon Carbide. SOVIET PHYS. - SOLID STATE, v. 5, no. 12, June 1964. p. 2500-2505.
- 17233 MAI, A. Free Carrier Absorption in n-Type Silicon Carbide. PHYS. SOC. OF JAPAN, J., v. 19, no. 8, Aug. 1964. p. 1486.
- 17374 WEEKS, J.L. and R.L. SEIFERT. Apparatus for the Measurement of the Thermal Conductivity of Solids. REV. OF SCI. INSTRUMENTS, v. 24, no. 11, Nov. 1953. p. 1054-1057.
- 17403 CARROLL, P. Resistivity of Granular Silicon Carbide - Impurity and Crystal Structure Dependence. In: CONF. ON SILICON CARBIDE, BOSTON, 1959. SILICON CARBIDE, A HIGH TEMPERATURE SEMICONDUCTOR, PROC., Ed. by O'CONNOR, J.R. and J. SMILTENS. N.Y., Symposium Pub. Div., Pergamon Press, 1960. p. 341-346.
- 17404 ADDAMIANO, A. Photoluminescence and Polytypism in Boron Doped Silicon Carbide. ELECTROCHEM. SOC., J., v. 111, no. 11, Nov. 1964. p. 1294.
- 17405 CHOYKE, W.J., et al. Optical Properties of Cubic Silicon Carbide. Luminescence of Nitrogen-Exciton Complexes, and Interband Absorption. PHYS. REV., v. 133, no. 4A, Feb. 17, 1964. p. A1163-A1166.
- 17406 SLACK, G.A. Thermal Conductivity of Pure and Impure Silicon Carbide and Diamond. J. OF APPLIED PHYS., v. 35, no. 12, Dec. 1964. p. 3460-3466.
- 17411 VASILIOS, T. and W.D. KINGERY. Thermal Conductivity: XI, Conductivity of Some Refractory Carbides and Nitrides. AMERICAN CERAM. SOC., J., v. 37, no. 9, Sept. 1954. p. 409-414.
- 17412 BLAU, H.H., JR. and J.R. JASPERSE. Spectral Emittance of Refractory Materials. APPLIED OPTICS, v. 3, no. 2, Feb. 1964. p. 281-286.
- 17414 FRIDEL, I. and G.F. KHOLOUYANOV. Electron Emission from p-n Junctions in Silicon Carbide Prepared by Nitrogen Diffusion. SOVIET PHYS. - SOLID STATE, v. 5, no. 7, Jan. 1964. p. 1418-1421.

- 17415 LIPSON, H.G. Infra-Red Transmission of alpha-Silicon Carbide. In: CONF. ON SILICON CARBIDE, BOSTON, 1959. SILICON CARBIDE, A HIGH TEMPERATURE SEMICONDUCTOR, PROC., Ed. by O'CONNOR, J.R. and J. SMILTENS. N.Y., Symposium Pub. Div., Pergamon Press, 1960. p. 371-375.
- 17416 POHL, R.G. Electrical Properties of beta-Silicon Carbide. In: CONF. ON SILICON CARBIDE, BOSTON, 1959. SILICON CARBIDE, A HIGH TEMPERATURE SEMICONDUCTOR, PROC., ED. by O'CONNOR, J.R. and J. SMILTENS. N.Y., Symposium Pub. Div., Pergamon Press, 1960. p. 312-330.
- 17417 CHOYKE, W.J. and L. PATRICK. Absorption of Light in alpha-Silicon Carbide Near the Band Edge. In: CONF. ON SILICON CARBIDE, BOSTON, 1959. SILICON CARBIDE, A HIGH TEMPERATURE SEMICONDUCTOR, PROC., Ed. by O'CONNOR, J.R. and J. SMILTENS. N.Y., Symposium Pub. Div., Pergamon Press, 1960. p. 306-311.
- 17419 PHILIPP, H.R. and E.A. TAFT. Intrinsic Optical Absorption in Single Crystal Silicon Carbide. In: CONF. ON SILICON CARBIDE, BOSTON, 1959. SILICON CARBIDE, A HIGH TEMPERATURE SEMICONDUCTOR, PROC., Ed. by O'CONNOR, J.R. and J. SMILTENS. N.Y., Symposium Pub. Div., Pergamon Press, 1960. p. 366-371.
- 17420 SPITZER, W.G., et al. Infra-Red Properties of Silicon Carbide. In: CONF. ON SILICON CARBIDE, BOSTON, 1959. SILICON CARBIDE, A HIGH TEMPERATURE SEMICONDUCTOR, PROC., Ed. by O'CONNOR, J.R. and J. SMILTENS. N.Y., Symposium Pub. Div., Pergamon Press, 1960. p. 376-382.
- 17421 ERIKSEN, W.T. Minority Carrier Lifetime in Silicon Carbide by Carrier-Injection Electroluminescence. In: CONF. ON SILICON CARBIDE, BOSTON, 1959. SILICON CARBIDE, A HIGH TEMPERATURE SEMICONDUCTOR, PROC., Ed. by O'CONNOR, J.R. and J. SMILTENS. N.Y., Symposium Pub. Div., Pergamon Press, 1960. p. 376-382.
- 17457 TOMASHPOLSKII, F.G. and G.F. KHOLOUYANOV. Concerning Recombination Radiation Spectra from Fused p-n Junctions in SiC. SOVIET PHYS. - SOLID STATE, v. 3, no. 9, Mar. 1962. p. 1960-1963.
- 17724 BRUEGEL, W. Strahlungsmessungen an elektrisch geheizten SiC-Staeben. Radiation Measurements on Electrically Heated Silicon Carbide Rods. ZEITSCHRIFT FUER PHYSIK, v. 127, no. 3, Mar. 17, 1950. p. 400-404.
- 17725 STANFORD RES. INST. Beta-Silicon Carbide and its Potential for Devices, by NELSON, W.E., et al. Final Rept. no. 21. Contract no. NObsr-87235. Dec. 31, 1963. DDC AD-428 005.
- 17730 VIOLIN, E.E. and G.F. KHOLOUYANOV. On the Electroluminescence and Photoluminescence of Diffused p-n Junctions in SiC. SOVIET PHYS. - SOLID STATE, v. 6, no. 6, Dec. 1964. p. 1331-1335.
- 17972 GRIFFITHS, L.B., et al. Silicon Carbide Diode Laser. IEEE PROC., v. 51, no. 10, Oct. 1963. p. 1374-1376.
- 17973 IGLITSYN, M.I., et al. Galvanomagnetic Effects in n-Type Silicon Carbide at Low Temperatures. SOVIET PHYS. - SOLID STATE, v. 6, no. 9, Mar. 1965. p. 2129-2135.

- 17974 PATRICK, L., et al. Luminescence of 4H Silicon Carbide, and Location of Conduction-Band Minima in Silicon Carbide Polytypes. PHYS. REV., v. 137, no. 5A, Mar. 1, 1965. p. A1515-A1520.
- 18056 DALVEN, R. Temperature Coefficient of the Energy Gap of beta-Silicon Carbide. J. OF PHYS. AND CHEM. OF SOLIDS, v. 26, no. 2, Feb. 1965. p. 439-441.
- 18349 LEUSHKINA, G.V., et al. Fluorescence of Silicon Carbide. AKADEMIIA NAUK UZBEKSKOI SSR. IZVESTIIA. SERIIA FIZIKO-MATEMATICHESKIH NAUK, v. 7, no. 6, 1963. p. 98-99.
- 18406 VAN DAAL, H.J., et al. Investigations on Silicon Carbide. J. OF APPLIED PHYS., v. 32, no. 10, Oct. 1961. p. 2225-2233.
- 18818 Kholuyanov, G.F. Polytypism and Recombination Radiation of p-n Junctions Prepared by the Diffusion of Boron in n-type Silicon Carbide. SOVIET PHYS. - SOLID STATE, v. 6, no. 11, May 1965. p. 2668-2671.
- 19150 BOSCH, G. On the Thermal Conductivity of Silicon Carbide. PHILIPS RES. REPTS., v. 16, no. 5, Oct. 1961. p. 455-461.
- 19560 NAT. BUREAU OF STANDARDS. DEPT. OF COMMERCE. Electroluminescence and Thermoelectricity, by HARMAN, G.G. and R.L. RAYBOLD. TR no. 1, AFCRC-TN-59-999. Dec. 1, 1959. DDC AD-220 814.

## PUBLICATIONS OF THE ELECTRONIC PROPERTIES INFORMATION CENTER (EPIC)

## Data Sheets

- DS-101 Cadmium Telluride. M. Neuberger. June 1962. (AD-415 331)
- DS-102 Indium Phosphide. M. Neuberger. June 1962. (AD-414 847)
- DS-103 Indium Telluride. M. Neuberger. June 1962. (AD-414 896)
- DS-104 Magnesium Silicide. M. Neuberger. June 1962. (AD-414 895)
- DS-105 Polyethylene Terephthalate. J.T. Milek. June 1962. (AD-414 846)
- DS-106 Polytetrafluoroethylene Plastics. E. Schafer. June 1962. (AD-413 907)
- DS-107 Polytrifluorochloroethylene Plastics. E. Schafer. June 1962. (AD-413 940)
- DS-108 Zinc Telluride. M. Neuberger. June 1962. (AD-413 939)
- DS-109 Indium Arsenide. M. Neuberger. June 1962. (AD-413 892)
- DS-110 Aluminum Antimonide. M. Neuberger. September 1962. (AD-413 676)
- DS-111 Gallium Phosphide. M. Neuberger. September 1962. (AD-413 954)
- DS-112 Gallium Antimonide. M. Neuberger. October 1962. (AD-413 775)
- DS-113 Lead Telluride. M. Neuberger. October 1962. (AD-437 311)
- DS-114 Magnesium Stannide. M. Neuberger. November 1962. (AD-413 825)
- DS-115 (No longer available - superseded by DS-144)
- DS-116 Lead Selenide. M. Neuberger. December 1962. (AD-437 310)
- DS-117 (No longer available - superseded by DS-137)
- DS-118 (No longer available - superseded by DS-137)
- DS-119 (No longer available - superseded by DS-137)
- DS-120 (No longer available - superseded by DS-137)
- DS-121 Indium Antimonide. M. Neuberger. February 1963. (AD-413 754)
- DS-122 Steatite. J.T. Milek. February 1963. (AD-413 834)
- DS-123 Beryllium Oxide. J.T. Milek. March 1963. (AD-413-831)
- DS-124 Cadmium Sulfide. Summary Review and Data Sheets. M. Neuberger. April 1963. (AD-413 667)
- DS-125 Magnesium Oxide. J.T. Milek. June 1963. (AD-413 809)

- DS-126 (No longer available - superseded by DS-137)
- DS-127 Silicone Rubber. J.T. Milek. June 1963. (AD-413 906)
- DS-128 Cordierite. J.T. Milek. June 1963. (AD-413 850)
- DS-129 Forsterite. J.T. Milek. August 1963. (AD-421 829)
- DS-130 Pyroceram. J.T. Milek. August 1963. (AD-421 883)
- DS-131 (No longer available - superseded by DS-143)
- DS-132 Zinc Selenide. M. Neuberger. September 1963. (AD-421 964)
- DS-133 Zinc Oxide. M. Neuberger. October 1963. (AD-425 212)
- DS-134 Cadmium Selenide. M. Neuberger. November 1963. (AD-425 216)
- DS-135 Zinc Sulfide. M. Neuberger and D.L. Grigsby. December 1963. (AD-427 288)
- DS-136 Aluminum Oxide. J.T. Milek. March 1964. (AD-434 173)
- DS-137 Silicon. M. Neuberger. May 1964. (AD-601 788)
- DS-138 Borosilicate Glasses. J.T. Milek. June 1964. (AD-602 773)
- DS-139 Aluminosilicate Glasses. J.T. Milek. July 1964. (AD-444 101)
- DS-140 Sulfur Hexafluoride. J.T. Milek. October 1964. (AD-607 949)
- DS-141 Niobium. D.L. Grigsby. November 1964. (AD-608 398)
- DS-142 Fluorocarbon Gases. J.T. Milek. November 1964. (AD-608 897)
- DS-143 Germanium. M. Neuberger. February 1965. (AD-610 828)
- DS-144 Gallium Arsenide. M. Neuberger. April 1965.
- DS-145 Silicon Carbide. M. Neuberger. June 1965.

Other Publications

EPIC BULLETIN. v. 1, no. 1, January 1965 - (published monthly)

- 5171.2/8 Information Retrieval Program. Electronic/Electrical Properties of Materials. First Quarterly Progress Report. E.M. Wallace. October 10, 1961. (AD-270 500)
- 5171.2/17 Information Retrieval Program. Electronic/Electrical Properties of Materials. Second Quarterly Progress Report. E.M. Wallace. January 15, 1962. (AD-271 926)

- 5171.2/32 Information Retrieval Program. Electronic/Electrical Properties of Materials. Third Quarterly Progress Report. E.M. Wallace. April 15, 1962. (AD-275 439)
- P62-18 Electrical and Electronic Properties of Materials Information and Retrieval Program. Final Report. H. Thayne Johnson, E. Schafer and E.M. Wallace. June 1962. (AD-289 546)
- S-3 A Survey Materials Report on Tetrafluoroethylene (TFE) Plastics. J.T. Milek. September 1964. (AD-607 798)
- S-4 The Purpose and Functions of the Electronic Properties Information Center. H. Thayne Johnson. August 1964.
- S-5 Electron Mobility in Aliphatic Hydrocarbons as Related to Organic Insulation Breakdown. J.T. Milek. February 1965.
- S-6 Optical Properties and Thermal Conductivity of Aluminum Oxide. M. Neuberger. February 1965.

AD numbers are furnished, when available, to facilitate your requesting publications from Defense Documentation Center (DDC), Cameron Station, Alexandria, Virginia 22314.